



SOVEREIGN CHEMICAL COMPANY

1225 West Market St., Akron OH 44313

Phone: 330-869-0500, Fax: 330-869-0518

www.sovchem.net

Antiozonant Dox 1 Pastilles

Manufacturer:


DJCHEM Chemicals Poland SA

Classification:

Diaryl-p-phenylene diamine antiozonant

Chemical Composition

Chemical Structure:



CA Nomenclature:

N'N-diaryl-paraphenylene diamine mixture

Chemical Synonyms:

Diaryl PPD, DTPD

Physical Data

Specification Properties

Specification Properties	Value	Test Method
Melting Point, °C	88.0-105.0	ASTM D 1519
Heat loss, % at 60°C	0.5 maximum	ASTM D 4571
Ash content, % at 525°C	0.5 maximum	ASTM D 4574
Active content, %	85.0 minimum	DJCHEM-210/04
Iron Content, ppm	750 maximum	DJCHEM-214/04

Typical Properties

Physical Form	Steel brown pastilles	Visual
Specific Gravity	1.18	Typical
Initial Melt Point, °C	88.0-97.0	ASTM D 1519

Application

Uses: Especially suited for products where outdoor weather resistance and heat resistance is needed. Recommended for tires, weather stripping, insulated wire/cables, hose, footwear, conveyor belts, O-rings, gaskets, seals, windshield wiper blades, motor mounts, automotive weather stripping, etc.

Protection: Excellent dynamic antiozonant and a good antioxidant that provides very long-term protection. It also protects against bin cure in CR. It also provides excellent high temperature heat degradation resistance, good flex crack resistance and protects against copper degradation.

Polymer: NR, SBR, BR, CR.

Synergism: Dox 1 Pastilles are often used with the dialkyl and alkyl/aryl p-phenylene diamines to provide optimized short-term and long-term protection.

Staining: Dox 1 Pastilles are the lowest staining and the least discoloring of the p-phenylene diamine type.

Cure Effect: Very slightly activating on the cure but the least activating of the p-phenylene diamine type antiozonants.

Recommended Dosage: As an antioxidant 1.0 phr. As an antiozonant 3.0 phr. Synergistic blend 1.0 phr dialkyl or alkyl/aryl p-phenylene diamine with 0.25 phr DOX 1.

Packaging and Storage

Packaging: 25 Kg (55.1 lb.) bags.

Shelf Life: 2 years from date of manufacture if stored as indicated below.

Storage: Store in original unopened packages in a cool dry environment.

Specification Date: July 13, 2011 (Supersedes: July 26, 2010)