



SOVEREIGN CHEMICAL COMPANY

1225 West Market St., Akron OH 44313

Phone: 330-869-0500, Fax: 330-869-0518

www.sovchem.net

Tartac 20 Liquid

Manufacturer: Mobile Rosin Oil Company

Classification: Pine tar plasticizer, tackifier and process aid

Chemical Composition: Pine Tar

Specification Data

Property	Value
Acid number	50 - 63
Viscosity, Stormer	8-20 RPM 24°C/50 gm. wt.
Appearance	Dark, viscous liquid
Moisture	1% Maximum
Specific Gravity	1.000 Typical
Ash	1.0% Maximum
Volatile Loss	7% Maximum (2 hours @ 105°C)

Applications: Low viscosity pine tar. Used as a plasticizer, tackifier, and process aid. Can also be used as a replacement for oil when economics or supply warrants. Due to the high acidity, pine tar will retard the cure; this can be offset by adding 3/4 phr of CaO.

Packaging and Storage

Packaging: 55 gal. (450 lb net) drums

Shelf Life: 4+ years from date of manufacture if stored as indicated below.

Storage: Store in original packaging in a cool dry place. Storing materials above 250°F will cause gradual decarboxylation. of the product.

Specification Date: September 23, 1994 (supersedes: new)