



SOVEREIGN CHEMICAL COMPANY

1225 West Market St., Akron OH 44313

Phone: 330-869-0500, Fax: 330-869-0518

www.sovchem.net

Tartac 30 Liquid

Manufacturer: Mobile Rosin Oil Company

Classification: Pine tar plasticizer, tackifier and process aid

Chemical Composition: Pine Tar

Physical Data

Specification Property	Value
Acid number	50 - 60
Viscosity, Stormer	100-200 secs. 30°C/400 gm. wt.
Moisture	0.5% Maximum
Specific Gravity	0.990 Typical

Typical Property	Value
Appearance	Dark, viscous liquid

Applications: Medium viscosity pine tar. Used as a plasticizer, tackifier, and process aid. Can also be used as a replacement for oil when economics or supply warrants. Due to the high acidity, pine tar will retard the cure; this can be offset by adding 3/4 phr of CaO.

Packaging and Storage

Packaging: 55 gal. (450 lb net) drums.

Shelf Life: 4+ years from date of manufacture if stored as indicated below.

Storage: Store in original packaging in a cool dry place. Storing materials above 250°F will cause gradual decarboxylation of the product.

Specification Date: February 25, 2011 (Supersedes: September 2, 1994).