

## Tartac 20 Liquid

Manufacturer: Mobile Rosin Oil Company  
Classification: Pine tar plasticizer, tackifier and process aid  
Chemical Composition: Pine Tar

Specification Properties	Value	Test Method
Acid Number	50-63	DCT 1022
Moisture, %	1.0 maximum	
Specific Gravity @25 °C	1 Typical	
Viscosity, Stormer @24 °C	8-20	

### > APPLICATIONS

**Uses:** Low viscosity pine tar. Used as a plasticizer, tackifier, and process aid. Can also be used as a replacement for oil when economics or supply warrants. Due to the high acidity, pine tar will retard the cure; this can be offset by adding 3/4 phr of CaO.

### > PACKAGING AND STORAGE

**Packaging:** 55 gal (450 lb.) drums

**Shelf Life:** 4+ years from date of manufacture if stored as indicated below.

**Storage:** Store in original packaging in a cool dry place. Storing materials above 250°F will cause gradual decarboxylation. of the product.

**Specification Date:** September 23, 1994